



EKOTEKS

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE



Test
TS EN ISO/IEC 17025
AB-0583-T

AB-0583-T

20032295

09-20

TEST REPORT
DENEY RAPORU

Customer name: DKC TEKNİK KAPLAMA APRE TEKSTİL VE DERİ SANAYİ VE
TİC.LTD. ŞTİ.
Address: BADIRGA MAH. (BURSA İHTİSAS DERİ OSB) AHİ EVRAN CAD.
NO:2-4 NİLÜFER/BURSA
Buyer name: -
Contact Person: BURÇİN DİKİCİ BORA / ATİKE KÖKEN
Order No: -
Article No: DB-Blackout
Name and identity of test item: One sample of white panel.
The date of receipt of test item: 04.09.2020
Re-submitted/re-confirmation date: -
Date of test: 04.09.2020-10.09.2020
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: Not Specified
Number of pages of the report: 5

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.

EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

Seal

Date
10.09.2020

Customer Representative
Özlem ULUS

Head of Testing Laboratory
Sevim A. RAZAK
10.09.2020

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

20032295

09-20

REQUIRED TESTS	RESULT	COMMENTS
MICROBIOLOGICAL TEST		
Antibacteria Activity/ <i>Staphylococcus aureus</i> ATCC 6538 (Gram(+))	-	
Antibacteria Activity/ <i>Klebsiella pneumonia</i> ATCC 4352 (Gram(-))	-	
No requirements were given by vendor.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. Tests marked (*) in this report are not included in the accreditation schedule.

Gen.f136-2/03



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

20032295

09-20

TEST RESULT

Test Method: AATCC 147:2016

(Antibacterial Assessment of Textile Materials: Parallel Streak Method)

Inhibition Zone (mm) ⁽¹⁾	Bacteria Growth ⁽²⁾	<u>Result</u>
5	None	Effective

Definition:

⁽¹⁾ Width of clear zone of inhibition in 5 (mm)

⁽²⁾ no bacterial colonies directly under the treated sample

Mikroorganism	<i>Staphylococcus aureus</i> ATCC 6538 (Gram(+))
Size of sample	25x50 mm
Incubation temperature	37°C±2°C
Incubation time	18-24 hours
Number of washing	-
Washing method	-

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

20032295

09-20

TEST RESULT

Test Method: AATCC 147:2016

(Antibacterial Assessment of Textile Materials: Parallel Streak Method)

Inhibition Zone (mm) ⁽¹⁾	Bacteria Growth ⁽²⁾	<u>Result</u>
0	None	Effective

Definition:

⁽¹⁾ Width of clear zone of inhibition in (mm)

⁽²⁾ no bacterial colonies directly under the treated sample

Mikroorganism	<i>Klebsiella pneumonia ATCC 4352 (Gram(-))</i>
Size of sample	25x50 mm
Incubation temperature	37°C±2°C
Incubation time	18-24 hours
Number of washing	-
Washing method	-